



1301 N. 3rd St. • Superior WI 54880 • 715-392-7114 • 800-373-2562 • F 715-392-7163 • www.twinportstesting.com

Appling County Pellets, LLC
 248 Sweetwater Drive
 Baxley, GA 31516

Date Received: 11/16/2009
Date Tested: 11/17/2009
Purchase Order #: 4884

Attn: Sandi McNeal

Sample Log Number: 09C3349

Sample Designation: #4915

	MOISTURE & ASH FREE	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Moisture Total			4.81	% wt.	ASTM E871
Ash		0.53	0.50	% wt.	ASTM D1102
Sulfur		0.010	0.009	% wt.	ASTM D4239
Heating Value	8444	8400	7996	Btu/lb	ASTM E711

	MDL	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Chlorine	10	37	35	mg/kg	ASTM D6721

	AS RECEIVED	UNITS		AS RECEIVED	UNITS
Bulk Density	44.50	lbs/cu.ft.	Fines	0.59	% wt.
Sample Above 1.50 In	0.0	%	Durability Index	95.8	
Maximum Length	1.190	inch	Stated Bag Wt.	40.0	lbs
Diameter, Range	0.288 to 0.300	inch	Actual Bag Wt.	40.3	lbs
Diameter, Average	0.294	inch			

Prepared By: *Sandi McNeal*

Date: 11/18/09